

Alpha-Fry™ EGS SAC0107, SAC0307, SAC0100, SAC0300

LEAD FREE SOLDER ALLOY

DESCRIPTION

Alpha-Fry™ EGS SAC0107 and EGS SAC0307 are low silver Pb-free solders suitable for wide soldering applications in industries. These low silver Pb-free solders show an excellent production yields which outperforms Sn/Cu based materials. These alloys have better solderability as a result of fast wetting speed than Sn/Cu alloys.

APPLICATION

Alpha-Fry™ EGS SAC0107 and EGS SAC0307 are suitable for wave and dipping soldering applications. These alloys may also be used in wire form for use in solder pot auto feed. A solder pot temperature of 255 - 265°C is recommended, depending on the soldering application and board designs.

Recommended top-up solder is EGS SAC0100 (for EGS SAC0107), EGS SAC0300 (for EGS SAC0307). Top-up relevant solder when the Cu% is $\geq 0.7\%$.

ALLOY COMPOSITION SPECIFICATION

Element	ALPHA-FRY EGS %			
	SAC0107 (Sn99.2Ag0.1Cu0.7)	SAC0307 (Sn99.0Ag0.3Cu0.7)	SAC0100 (Sn99.9Ag0.1)	SAC0300 (Sn99.7Ag0.3)
Sn	Balance	Balance	Balance	Balance
Ag	0.10 -0.02/+0.20	0.3 +/- 0.1	0.10 -0.02/+0.20	0.3 +/- 0.1
Cu	0.7 +/- 0.1	0.7 +/- 0.1	0.050 max	0.050 max
Pb	0.100 max	0.100 max	0.100 max	0.100 max
Sb	0.100 max	0.100 max	0.100 max	0.100 max
Zn	0.001 max	0.001 max	0.001 max	0.001 max
Fe	0.020 max	0.020 max	0.020 max	0.020 max
As	0.030 max	0.030 max	0.030 max	0.030 max
Ni	0.010 max	0.010 max	0.010 max	0.010 max
Bi	0.100 max	0.100 max	0.100 max	0.100 max
Cd	0.002 max	0.002 max	0.002 max	0.002 max
Al	0.001 max	0.001 max	0.001 max	0.001 max
In	0.050 max	0.050 max	0.050 max	0.050 max
Au	0.050 max	0.050 max	0.050 max	0.050 max

AVAILABLE PACKAGING

Alpha-Fry™ EGS is available in bars, 20kg per box. For other metal forms requirement, please contact our Sales Department.

HEALTH & SAFETY

Please refer to MSDS for advice on proper handling and safety instructions.

STORAGE

Store the solder bar in a cool, dry and non-corrosive environment. Wrap up the solder bar when not in use to reduce exposure to environment.



SHELF LIFE

Alpha-Fry™ EGS can be kept for 5 years, if proper storage conditions are observed. After certain period of storage, the solder surface shininess may reduce and a dull shade of gray or light yellow may appear. However, this is only a surface phenomenon and will not affect the product functionality.